

# ChemLINE® 784 WS

## Wine and Spirits



*A coating with superior chemical resistance and high temperature resistance, based on an Ethanol solvent formulation.*

### Description

ChemLINE® WS (Wine and Spirits) is a high functionality, two component thermoset polymer coating formulated with ethanol as the reduction solvent. ChemLINE® WS assures that no hydrocarbon contamination can occur in alcohol cargoes from the lining. ChemLINE® WS is formulated with a unique polymer, that when polymerized, cross links up to 784 times per molecule. This results in a virtually impermeable, highly chemical resistant coating.

#### ChemLINE® WS's higher cross link density and alcohol solvent formulation means:

- ▶ Outstanding chemical resistance to alcohols, acids, caustics and solvents
- ▶ High heat resistance
- ▶ High abrasion resistance
- ▶ No risk of hydrocarbon contamination of cargoes
- ▶ Suitable for food cargoes

#### Provides Superior Chemical Resistance to:

- ▶ Ethanol
- ▶ Methanol
- ▶ 98% Sulfuric Acid
- ▶ 37% Hydrochloric Acid
- ▶ 50% Sodium Hydroxide
- ▶ Methylene Chloride
- ▶ Acetic Acid
- ▶ Most acids, alkalis and solvents

### Industry Applications

- ▶ **Food Processing** – Alcohol containing products such as wine and spirits
- ▶ **Transportation** – Rail, Truck, Marine
- ▶ **Storage Vessels**
- ▶ **Bio-Fuel and Alcohol Processing**
- ▶ **ISO tanks, OTR tankers, railcars and barges carrying alcohol based cargoes**

### Product Highlights

- ▶ No hydrocarbon contamination of cargoes
- ▶ Superior corrosion resistance, exceptional toughness
- ▶ Superior bonding qualities
- ▶ Can be applied to pitted and/or corroded steel
- ▶ Maximum versatility; product cycling
- ▶ Ambient or lower temperature forced air cure
- ▶ Low VOC - 104 grams/L (0.87 lbs./ gal.)
- ▶ Virtually impermeable, steam cleanable, & field repairable
- ▶ Resists hydroblasting
- ▶ High impact resistance
- ▶ Dry heat resistance to 400° F (204° C)
- ▶ ChemLINE® WS is generally recognized as safe (GRAS) for use in food contact applications in the United States\*
- ▶ BPA Free
- ▶ Resistant to broad range of CIP detergents & percentages

### Typical Properties (mixed, as supplied)

- ▶ Stock Colors \_\_\_\_\_ Gray, White
- ▶ VOC Level \_\_\_\_\_ 104 grams/L (0.87 lbs./gal.)
- ▶ Pot Life \_\_\_\_\_ 30 minutes @ 75°F (24°C)
- ▶ Viscosity Reduction \_\_\_ Reduce with 200 proof Ethanol ONLY
- ▶ Solids by Volume \_\_\_\_\_ 87%
- ▶ Recommended Film Thickness (dry) mils average \_\_\_\_\_ Steel: 12-14mils (300-350 microns)
- ▶ Shelf Life \_\_\_\_\_ 12 months

*For product recommendations and technical, application and heat curing information contact Advanced Polymer Coatings' customer service. Contact +1 440-937-6218.*



\*contact a ChemLINE® representative for details on specific applications

# ChemLINE® 784 WS

## Wine and Spirits



The information provided by Advanced Polymer Coatings, Inc. (APC) for the application or repair of APC coatings is based upon protective coating industry standards and knowledge gained through observation of professional applicators throughout the world that have successfully applied APC coatings. APC does not exercise any control over selection of the applicator that applies or repairs APC coatings. By providing information APC is not representing, directly or by implication, that an applicator that is provided with this information will achieve a result that will pass without objection in the trade or industry, otherwise referred to as MERCHANTABILITY, or will meet the vessel owner's protective coating requirements, otherwise referred to as FITNESS FOR A PARTICULAR PURPOSE. The only warranty provided by APC through its information and literature is that all APC products when delivered will have been manufactured in accordance with APC's manufacturing procedures, will be accurately labeled, and when mixed, applied and cured in a controlled environment in accordance with APC's current written application guidelines will withstand chemical corrosion as set forth in APC's chemical compatibility reference guide. The chemical compatibility reference guide and

### Advanced Polymer Coatings

Avon, Ohio 44011 U.S.A.

+1 440-937-6218 Phone

800-334-7193 Toll-Free USA & Canada



current application guidelines are available at [www.adv-polymer.com](http://www.adv-polymer.com). Any customer specific express warranty can only arise from a written warranty extended by APC to the specific customer identified in the writing. APC DISCLAIMS ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE THAT ARE CONTAINED IN ARTICLE 2 OF THE UNITED STATES UNIFORM COMMERCIAL CODE AND ANY SIMILAR WARRANTIES CONTAINED IN THE LAWS OF OTHER COUNTRIES WHERE APC PRODUCTS ARE DELIVERED OR APPLIED. ALL CONTRACTS FOR THE SALE OF APC PRODUCTS SHALL BE GOVERNED BY THE UNIFORM COMMERCIAL CODE WITHOUT REGARD TO ANY STATE VARIATIONS.

© Copyright 2024-04-03

[www.adv-polymer.com](http://www.adv-polymer.com)

TOMORROW'S SOLUTIONS TODAY